

CHEMICAL MILLING does not, in any way, alter the molecular structure nor the mechanical properties of the processed lamina.


La **FOTOTRANCIATURA CHIMICA** non altera in alcun modo la struttura molecolare, nè le proprietà meccaniche del particolare lavorato.

Min. Cut Out (Holes or Slots)

Metal Thickness (T)	Min. hole size
< 0.15mm	0.15mm
≥ 0.15mm	T

Etched Dimension Tolerance

Metal Thickness (T)	Tolerance
< 0.25mm	±0.025mm
≥ 0.25mm	±10% of T



Section AA

Typical Edge Profile when Etched from both sides

Cusp = 10% T

